

**JP 58126679**

2/9/1

DIALOG(R) File 347:JAPIO

(c) 2003 JPO & JAPIO. All rts. reserv.

01189279 \*\*Image available\*\*

**FORMATION OF ELECTRODE FOR THIN-FILM LITHIUM BATTERY**

PUB. NO.: 58-126679 [JP 58126679 A]

PUBLISHED: July 28, 1983 (19830728)

INVENTOR(s): KANEBORI KEIICHI

MIYAUCHI KATSUMI

KUDO TETSUICHI

APPLICANT(s): HITACHI LTD [000510] (A Japanese Company or Corporation), JP  
(Japan)

APPL. NO.: 57-007595 [JP 827595]

FILED: January 22, 1982 (19820122)

INTL CLASS: [3] H01M-010/40

JAPIO CLASS: 42.9 (ELECTRONICS -- Other)

JOURNAL: Section: E, Section No. 205, Vol. 07, No. 236, Pg. 139,  
October 20, 1983 (19831020)

**ABSTRACT**

PURPOSE: To obtain an electrode, which has an excellent electric contact and a high mechanical adhesion, by interposing beforehand a film made of the original metal of a positive electrode material between the positive electrode material and a positive current-collecting body of a thin-film lithium battery, the positive electrode of which is prepared from a metal chalcogenide or a metal oxide.

CONSTITUTION: After a titanium film 2 with about 0.1. $\mu$ m thickness is formed on an iron plate 1 with 0.4mm thickness, TiS(sub 2) is formed on the film 2 into a film 3 of around 3. $\mu$ m thickness by the CVD method. Next, a solid electrolyte material represented by the formula, (1-X)Li(sub 4)SiO(sub 4)XLi(sub 3)PO(sub 4) (0<X<1), is formed over the film 3 into a film 4 with around 2. $\mu$ m thickness by sputtering. After that, lithium is formed on the film 4 into a film 5 with around 1. $\mu$ m thickness by a vapor-deposition method, thereby obtaining a basic structure for a thin-film lithium battery. As a result of measurement carried out in a dry atmosphere on the basic characteristics of the battery such as open-circuit voltage and short-circuit current, at room temperature, an open-circuit voltage of 2.4V and a short-circuit current of 3mA/cm(sup 2) were obtained.